

Hohlwellen ind. gehärtet HRC 62	Innen Ø	Herstellängen max.	Einhärtetiefe max.	Aussen Ø Tolreanz ISO h6
aus 100Cr6				
Wellen Ø				
12	4	6000	1,3	0 -11
16	7	6000	1,6	0 -11
20	14	6000	1,6	0 -16
25	15,5	6000	1,8	0 -16
30	18	6000	2	0 -16
40	28	6000	2,5	0 -19
50	29,7	6000	3	0 -19
60	36	6000	3	0 -19
80	57	6000	3,2	0 -19